

LIGHTWEIGHT CONCRETE WITH STYROFOM BEADS

STYROFOM - FILLED LIGHTWEIGHT CONCRETE DIFFERS FROM OTHER FORMS OF LIGHTWEIGHT CONCRETE BECAUSE OF THE SPECIAL PROPERTIES OF THE PRE-EXPANDED STYROFOM BEADS. THESE BEADS OCCUPY 60 - 80 % OF THE VOLUME, DEPENDING ON THE DENSITY OF CONCRETE THE STYROFOM BEADS FORMING THE AGGREGATE HAVE THE FOLLOWING PROPERTIES.

- 1- EXTREMELY LOW APPARENT DENSITY.
- 2- OUTSTANDING LOW THERMAL CONDUCTIVITY.
- 3- NEGLIGIBLE MOISTURE UPTAKE BECAUSE OF THE CLOSED CELLULAR STRUCTURE.
- 4- REGULARLY SPHERICAL FORM LEADING TO THE FORMATION OF THE CEMENT MATRIX WITH COMPARATIVELY HIGH COMPRESSIVE STRENGTH. THE LIGHTWEIGHT CONCRETE DENSITY RANGES BETWEEN 300 AND 900 Kg/M³. THE DENSITY IN THE REGION OF 600 Kg/M³ IS THE MOST ADEQUATE DENSITY FOR LIGHTWEIGHT CONCRETE. AT THIS DENSITY THERE IS SUFFICIENT CEMENT TO FILL THE INTERSTITIAL SPACES BETWEEN THE STYROFOM BEADS, AND ENOUGH STRENGTH IN THE CONCRETE. THE MOST SUITABLE DENSITY OF THE STYROFOM BEADS IS ABOUT 13-14 Kg/ M³.

COMPOSITION OF LIGHTWEIGHT CONCRETE MIXES USING STYROFOM BEADS

Density of concrete Kg/M ³	CEMENT Kg	SAND Kg	WATER Kg	Compression Resistance Kgf/CM ²	Flexure Resistance Kgf/CM ²
200	150	---	50	---	---
300	200	---	100	3	2
400	250	25	125	7	4
500	300	50	150	14	6
600	350	100	150	20	7
700	350	175	175	32	8
800	350	250	200	45	10
900	375	325	200	60	12